

PRODUCT BULLETIN
GYPSUM PRODUCTS

GYPSUM BOARD
1/2" REGULAR

BULLETIN NO: B-3
DATE: 12/1/77
PAGE: 2 of 2

APPROVALS:

A.S.T.M. C 36

CANCELS: B-3
DATE: 9/12/75

PRODUCING PLANTS: Long Beach, Antioch, Seattle

PRODUCT SPECIFICATIONS: (Refer to Product Bulletin B-G-4 for General Finished Product Specifications).

	Acceptance Limits		Control Values		
	Min.	Max.	Min.	Std.	Max.
Wet Weight (lbs/MSF)			2600		2875
TAKE-OFF TESTS					
Dry Weight (lbs/MSF)*	1650	1825	1700	1750	1850
Evaporation Loss (lbs/MSF)			700		900
Thickness, Average (inch)	0.484	0.516	0.484	0.490	0.510
Thickness, indiv. rdg. (inch)	± 0.010 from avg.		± 0.010 from average.		
Twist Test, tested hot face & back (inch)				0	2
End Peel, tested @ 1-2 hours face and back (inch)				0	1
Bond Test, tested @ 1-2 hours face and back (inch)		2		0	1
Falling Ball Impact (inch)			0.020		0.050
Edge Hardness (lbs)	8		10	14	18

STANDARD CONDITIONED SAMPLE TESTS

Flexural Strength, (lbs)					
Across			140	150	
Parallel	40		40	50	
Deflection @ Break (inch)					
Across	0.30		0.30	0.35	
Parallel	0.20		0.20	0.25	
Punch Test (lbs)	550	900	550	600	900
End Peel after Sawing		1		0	1/2
Twist Test (inch)					
face and back		2		0	1
High Humidity Bond (inch)					
face and back		1		0	1
Nail Pull Resistance	80		80	90	

* NOTE: Board manufactured outside the specified dry weight ranges may be shipped provided board conforms to all other finished product specifications.